
Name	(pin	yin	please)
------	------	-----	--------	---

Homework #2. If you get your work to me by Monday evening, we can discuss it in class Tuesday morning....before the exam on Wednesday.

It will be OK if you want to email your work to me at rx7@psu.edu

1. Construct the two point group diagrams for the point group 32.




2. CaF_2 is Fm3m, a = 5.462 Å, Ca in 4 a, F in 8c. Make a drawing of the crystal structure projected down [001]. The equipoints for space group Fm3m are listed on the next page.

The F atoms have how many Ca nearest neighbors (i.e., how many Ca atoms touch each F atom)?

Since a = 5.462 Å, what is the Ca-F bond distance? (A simple geometry calculation.)

Posit	ions		,	Con	ardinatas		2 3230	100000000
Multiplicity, Wyckoff letter, Site symmetry		+(0,0,0)	Coordinate $(0,\frac{1}{2},\frac{1}{2})+$		+,0,1)+	(1,1,0)+		
192	1	1 (1) (5) (9) (13) (17) (21) (25) (29) (33) (37) (41)	(1) x,y,z (5) z,x,y (9) y,z,x (13) y,x,\(\bar{z}\) (17) x,z,\(\bar{y}\) (21) z,y,\(\bar{x}\) (25) \(\bar{x}\),\(\bar{y}\),\(\bar{z}\) (29) \(\bar{z}\),\(\bar{x}\),\(\bar{z}\) (33) \(\bar{y}\),\(\bar{z}\),\(\bar{x}\) (41) \(\bar{x}\),\(\bar{z}\),\(\bar{y}\),\(\bar{x}\)		, \$\bar{y}\$ (1), \$\bar{x}\$ (1), \$\bar{z}\$ (1); \$\bar{z}\$ (1); \$\bar{z}\$ (1); \$\bar{y}\$ (2); \$\bar{z}\$ (2), \$\bar{z}\$ (2), \$\bar{y}\$ (3), \$\bar{x}\$ (3), \$\bar{y}\$ (4)	3) \$\begin{align*} \pi, y, \bar{z} \\ \bar{z}, \bar{x}, y \\ \bar{z} \\ \bar{z}, \bar{x}, y \\ \bar{z}, \bar{z}, \bar{x} \\ \bar{z}, \bar{z}, \bar{y} \\ \bar{z}, \bar{z}, \bar{y} \\ \bar{z}, \bar{y}, \bar{z}, \bar{z}, \bar{z} \\ \bar{z}, \bar{z}, \bar{z} \\ \bar{z}, \bar{z}, \bar{z}, \bar{z} \\ \bar{z}, \bar{z}, \bar{z}, \bar{z}, \bar{z} \\ \bar{z}, \b	(4) x, y, z (8) z, x, y (12) y, z, x (16) y, x, z (20) x, z, y (24) z, y, z (32) z, x, y (36) y, z, z (40) y, x, z (44) x, z, y (48) z, y, x	
96	k	m	X, X, Z $\overline{Z}, \overline{X}, X$ X, X, \overline{Z} $\overline{X}, \overline{Z}, \overline{X}$	\bar{x}, \bar{x}, z \bar{z}, x, \bar{x} $\bar{x}, \bar{x}, \bar{z}$ x, \bar{z}, x	\bar{x}, x, \bar{z} x, z, x x, \bar{x}, z z, x, \bar{x}	$\begin{array}{c} x, \overline{x}, \overline{z} \\ \overline{x}, z, \overline{x} \\ \overline{x}, x, z \\ z, \overline{x}, x \end{array}$	z,x,x x,\bar{z},\bar{x} x,z,\bar{x} \bar{z},x,x	z, X, X X, Z, x X, z, x Z, X, X
96	j	m	0, y, z z, 0, y y, 0, z 0, z, y	$0, \bar{y}, z \\ \bar{z}, 0, \bar{y} \\ \bar{y}, 0, \bar{z} \\ 0, \bar{z}, y$	0, y, z y, z, 0 y, 0, z z, y, 0	0, ỹ, ἔ ỹ, z, 0 ỹ, 0, z z, ỹ, 0	z,0,y y,z,0 0,z,ÿ z,y,0	z,0,ÿ ÿ,z,0 0,z,y z,ÿ,0
48	i	m .m 2	½.y.y ÿ.½.y	$\frac{1}{2}$, \bar{y} , y \bar{y} , $\frac{1}{2}$, \bar{y}	$\frac{1}{2}$, y , \overline{y} y , y , $\frac{1}{2}$	½,ÿ,ÿ ÿ,y,½	y.½.y y,ÿ,½	y.½.ÿ y,y,½
48	h	m .m 2	0,y,y ÿ,0,y	$_{\bar{y},0,\bar{y}}^{0,\bar{y},y}$	$0, y, \overline{y}$ y, y, 0	0, ỹ, ỹ ỹ, y, 0	y,0,y y,5,0	y,0,ÿ ÿ,ÿ,0
48	g	2 .m m	$X, \frac{1}{4}, \frac{1}{4}$ $\frac{1}{4}, X, \frac{3}{4}$	$\bar{X}, \frac{3}{4}, \frac{1}{4}$ $\frac{3}{4}, \bar{X}, \frac{3}{4}$	$\frac{1}{4}, x, \frac{1}{4}$ $x, \frac{1}{4}, \frac{3}{4}$	$\begin{array}{c} \frac{1}{4}, \overline{X}, \frac{1}{4} \\ \overline{X}, \frac{1}{4}, \frac{1}{4} \end{array}$	$^{\frac{1}{4},\frac{1}{4},x}_{\frac{1}{4},\frac{1}{4},\tilde{x}}$	$\frac{1}{4}, \frac{1}{4}, \overline{x}$ $\frac{1}{4}, \frac{1}{4}, x$
32	f	. 3 <i>m</i>	$x, x, x \\ x, x, \bar{x}$	\vec{x}, \vec{x}, x $\vec{x}, \vec{x}, \vec{x}$	\bar{x}, x, \bar{x} x, \bar{x}, x	$x, \bar{x}, \bar{x} \\ \bar{x}, x, x$		
24	e	4m.m	x,0,0	x,0,0	0,x,0	0,1,0	0,0,x	7,0,0
24	d	m.mm	$0, \frac{1}{4}, \frac{1}{4}$	0,1,1	1,0,1	1,0,1	1,1,0	1,1,0
8	c	43m	1,1,1	1,1,1				
4	b	m 3m	1,1,1					
4	a	m 3m	0,0,0					

3. A monoclinic crystal has a = 6, b = 4, c = 10 Å, β = 110°. Make a rough drawing of a portion of the k = 0 level of the reciprocal lattice. Show and name the reciprocal lattice vectors and angle for the reciprocal lattice unit cell.
4. In a powder diffractometer, give the function (tell what it does) of the:
divergence slit
receiving slit
Soller slits
monochromator
5. Index this cubic powder diffraction pattern on the next page.
Give the Bravais lattice.
Calculate the lattice parameter for this material. Show your calculations. λ = 1.54184 Å.



	_
20	d (A)
19.279	4.6000
22.319	3.9800
31.703	2.8200
37.473	2.3980
39.169	2.2980
45.569	1.9890
49.960	1.8240
51.345	1.7780
56.667	1.6230
60.457	1.5300
66.440	1.4060
69.937	1.3440
75.654	1.2560
79.947	1.1990
84.195	1.1490